E^xponent[®]



Samsung Recall Support Note7 Investigation

Root Cause Analysis


Kevin White, PhD Principal Scientist 23 January 2017

E^{x} ponent°

Background and Project Scope

- After reports of failures in the field, Exponent was retained as an independent third-party to investigate the root cause for thermal failures of Note7 lithium-ion battery cells
- A suite of destructive and non-destructive techniques was used to evaluate the field failure and exemplar cells from both manufacturers that provided cells to Samsung
- In addition to analysis of the cells, an analysis of the design of the battery, device and electronics was conducted







SAMSUNG

ENSAMBLADO EN CHINA / MONTADO NA CHINA 제조자 : Ningde Ameperex Technology Limited MADE IN CHINA / FABRIQUÉ EN CHINE

Secondary Li-ion Battery / 리튬이온2차전지 / 제품명 : 전지 A/S 문의 전화번호:1588-3366 3500 mAh 13.48 Wh Charge Voltage / 충전전압 / 充電電圧: 4.4 V == Nominal Voltage / 공칭전압 / 定格 : 3.85 V == 11CP6/39/98



PS











EB-BN930ABA


제조년월: S/N:





 \mathbf{E}^{χ} ponent

Root Cause: Manufacturer A

- Based on the results of analysis and testing, the most likely root cause for the thermal failure of certain Manufacturer A cells was determined to be unintended damage to the negative electrode windings consistently in the corner of the cell closest to the negative tab
 - The unintended damage was present in all of the cells examined by Samsung and Exponent
 - The damage was caused by a cell pouch design that provided inadequate volume to accommodate the electrode assembly
 - The observed damage provides multiple potential routes to internal cell faulting and thermal failure with normal cycling, including compromise of the separator and lithium plating
- Exponent's initial analysis of cells from Manufacturer B showed no deficiencies in the pouch, design or manufacturing
 - Manufacturer B cells manufactured after our initial investigation was complete were shown to contain a distinctly different defect that was not present in the initial cells we investigated







Root Cause: Manufacturer B

- Based on the results of analysis and testing, the most likely root cause for the thermal failure of Manufacturer B cells was determined to be internal cell faulting between positive electrode tab welding defects and the copper foil of the negative electrode directly opposite the defective welds
 - Welding defects in some incident cells were found to be tall enough to bridge the distance to the negative electrode foil
 - Some cells examined were assembled without protective tape over the positive electrode tab, increasing the likelihood of an internal cell fault

Positive Tab



Negative Electrode Opposite Positive Tab





 Poorly controlled welding of the positive tab in Manufacturer B cells creates sharp, relatively tall welding defect features

 Normal swelling and contraction of the electrodes during charge and discharge forces the weld defect features into the opposing negative electrode

 Short circuit between the weld defect feature on the positive tab and the copper of the negative electrode results in heating of the cell

 At high states of charge, the cell heating results in thermal run away.






Battery System Analysis

- Analysis of the Note7 battery system design indicated that the system is designed with multiple levels of protection for the Li-ion cell
- The testing and analysis performed did not identify a fault in the Note7 battery system that could have triggered the observed battery failures in the field
- Testing performed with several third party wireless charging pads available for use with the Note7 device showed that the Note7 device is designed to prevent a failure of these charging pads from causing the Li-ion cell to operate outside its specifications

Note7 Battery System Architecture



Exponent® Engineering & Scientific Consulting

